



# Technical Data Sheet

## CLEARTOP MT300

### TuttoChromaMe™ TC series Chrome spay-on coating

#### SERVICES

##### Technical Support

Is available on line 24/7

Tel: +39-3311699006

Email: [support@chromame.it](mailto:support@chromame.it)

##### Application Support

##### Live demo at

ChromaMe Italy

ChromaMe Dubai

Make an appointment

Italy: +39-3311699006

Dubai: +971 55820 7649

Email: [support@chromame.it](mailto:support@chromame.it)

##### Commercial Inquiries

- Training

- Installation and setup

- On line support

Get in touch Whatsapp

Italy: +39 3311699006

Dubai: +971 558207649

Qatar: +971 509594511

Email: [info@chromame.it](mailto:info@chromame.it)

For more information on any of our products or services please visit us on the Web at:

[www.chromame.it](http://www.chromame.it)



ChromaMe Nano Tech Srls

Via Ernesto Casagrande 16 10078

VENARIA REALE (TO) Italy

P.IVA/VAT n. IT02840170811

#### DESCRIPTION

|              |                |
|--------------|----------------|
| Product Name | CLEARTOP MT300 |
| Product Code | TUT.TOP.MT300  |

#### PHYSICAL FEATURES AT SUPPLY

|                  |                                 |
|------------------|---------------------------------|
| Binder type      | Polyacrylic                     |
| Apperance        | Glossy- medium viscosity liquid |
| Colour           | Transparent                     |
| Supply Vx        | 23 ± 3" CF/4 at 20°C            |
| Specific Density | 0,960 ±0,030 Kg/l at 20°C       |
| Dry residue      | 37 ± 2%                         |

#### APPLICATION FEATURES

|                       |                                                                     |
|-----------------------|---------------------------------------------------------------------|
| Hardener              | CLEARCATALYST MT934                                                 |
| Product Code          | TUT.CAT.MT934                                                       |
| Mix ratio             | 5:2 40% in weight                                                   |
| Coloring              | TUTTOCHROMAME Pigments can be added, see Application video tutorial |
| Application viscosity | 17± 2" CF/4 at 20°C                                                 |
| Application tools     | HVLP Airless spray - only PROFESSIONAL USE                          |
| Spay gun parameters   | Nozzle tip 1,2 -1,5 mm Pressure at nozzle 3,00 bar /435,1 psi       |
| Layer numbers         | 2 alternate layers                                                  |
| Pot -life             | ~ 2 hours at 20°C                                                   |
| Withering             | 10 minutes at 20°                                                   |
| Curing Cycle          | 60 minutes at 60°C or 24-36 hours at ambient temperture 20° C       |

#### DRY PRODUCT FEATURES

|                    |                                                                             |
|--------------------|-----------------------------------------------------------------------------|
| Support            | any material provided that the sufurce is coated with suitable base coating |
| Dry film thickness | 30 ± 5 µm                                                                   |
| Finish             | 99 Gloss                                                                    |
| Hardness           | F-H total harding after 24-36 in open air room temp                         |
| Coverage           | 5-6 sq.m./litre coat                                                        |

#### STORAGE INSTRUCTIONS

|                     |                                                                                               |
|---------------------|-----------------------------------------------------------------------------------------------|
| Packaging           | Tin cans 1kg ; 5kg ; 20 kg                                                                    |
| Shelf life          | Storage temperature min 3°C max 40°C - keep away from direct sunlight                         |
| Product Stability   | CLEARTOP MT300 5 years in original package<br>CLEARCATALYST MT934 3 years in original package |
| Safety Instructions | Read MSDS Material safety data sheet carefully before using products                          |



Scan for VIDEO  
Application Tutorial



Scan for ADS  
Application  
Datasheet



Scan for MSDS  
Material Safety  
Datasheets

DISCLAIMER: The above information provided herein is based on the present state of our knowledge and practical experience. Since the product is often used under different conditions beyond our control. We cannot guarantee anything but the quality of the product itself. All the rights are reserved to change the data without any notice.

Date Issued 6 March 2023 Revision 5